

XSYS

Print solid. Stay flexible.

nyloflex[®] Seal F

Film based coating plate
for print finishing



Be
brilliant.


PRODUCT FEATURES

- **Especially developed** for inline finishing in sheetfed offset presses with flexo coating units and for offline finishing in coating presses.
- **For spot and full surface coating** in commercial and packaging printing on coated papers and board.
- **Excellent stability** even with UV coatings and UV inks.
- **High contrast** colour change.
- **Excellent dimensional stability** due to thick polyester film.
- **Wide exposure** latitude.
- **High resolution.**
- **Very good transfer** of water based dispersion and UV varnishes.
- **High print contrast.**



ADVANTAGES OF NYLOFLEX® SEAL F DIGITAL

- **Superior printing quality** with sharper images, more open intermediate depths.
- **Ideal for the coating** of finest details.
- **Consistency in quality** for repeating jobs.




Be
brilliant.

nyloflex® Seal F


nyloflex® Seal F plates are monolayer plates. They consist of a light sensitive photopolymer layer bonded to a polyester film.



nyloflex® Seal F Conventional



nyloflex® Seal F Digital



**MAKE YOUR BRAND
MORE BRILLIANT
WITH A HIGH
QUALITY
& RELIABLE COATING**

nyloflex® Seal F

Photopolymer film based coating plate for inline and offline print finishing

Technical characteristics	nyloflex® Seal F	nyloflex® Seal F Digital
	116	116
Base material	polyester film	polyester film
Colour of raw plate	violet	violet, with black LAMS layer
Total thickness ¹ (mm) (inch)	1.16 (0.046")	1.16 (0.046")
Hardness acc. to DIN 53505 (Shore A)	50	50
Plate hardness (Shore A)	72	72
Relief depth (mm)	0.9	0.9
Tonal range (%)	3-90	2-95
at screen ruling of (l/cm)	48 l/cm (122 lpi)	48 l/cm (122 lpi)
Fine line width (down to µm)	300	300
Isolated dot diameter (down to µm)	750	750
Elongation constant (mm)	5.72	5.72

Processing parameters ²		
Back exposure (s)	10-12	10-12
Main exposure (min)	10-15	8-12
Washout speed (mm/min)	100-130	100-130
Drying time at 60°C / 140°F (h)	2	2
Post exposure UV-A (min)	10	10
Light finishing UV-C (min)	6-10	6-10

Processing information

Suitable equipment	The nyloflex® Seal F can be processed with nyloflex® processing equipment and all similar devices. The nyloflex® Seal F Digital can be used with all laser systems suitable for imaging flexo printing plates.
Printing inks	nyloflex® Seal F and nyloflex® Seal F Digital coating plates are suited for water based dispersion and UV varnishes.
Washout solvents	Especially good results are achieved with nylosolv® washout solvents. nylosolv® can be distilled and reused.
Processing information	A detailed description of the individual platemaking steps, as well as detailed information about processing and storing can be found in the nyloflex® User Guide.
Certification	XSYS printing plates are produced at Willstätt production site, which is certified according to international standards for quality management (DIN EN ISO 9001:2015), environmental management (DIN EN ISO14001:2015) and energy management (DIN EN ISO 50001:2018).

1) Standard thicknesses currently available – subject to change 2) All processing parameters depend on, among other things, the processing equipment, lamp age and the type of washout solvent. A minimum exposure intensity of $\geq 17 \text{ mW/cm}^2$ is recommended. The above mentioned processing times were established under optimum conditions in our technical center. The standard test file with 149lpi was imaged at 400DPI using a ThermoFlexX imager, 20 mW/cm² bank exposure, using nylosolv® A washout solvent and nyloflex® and ThermoFlexX Catena plate processing equipment. Under other conditions the processing times can differ from these; therefore, the above mentioned values are only to be used as a guide. 3) Depending on longevity of the tubes. 4) Suitability with UV inks is dependant on the ink type and temperature – these factors could affect the performance of the plate and consistency of the print.

Please contact us for additional information.

info@xsysglobal.com • www.xsysglobal.com

Our technical documents are designed to inform and guide our customers. The information provided herein is accurate to the best of XSYS's knowledge; however, we accept no liability for any errors, inaccuracies, or opinions expressed. Customers are responsible for determining the suitability of this product for their specific application. XSYS assumes no responsibility for any loss incurred as a result of reliance on the information contained in this document. Product names followed by ® are registered trademarks of XSYS Germany GmbH and/or its affiliates.

XSYS

Print solid. Stay flexible.