

nyloprint® S

Alcohol washable gravure plate for high print quality

Be
brilliant.



Product features

- + **Wide range of applications**
 - + Photopolymer gravure plate for high quality pad printing, suitable for printing on promotional and industrial products
 - + nyloprint® S43 and S58 also suitable for letterset, form printing on continuous letterset presses, label printing, metal sheet printing, sheetfed and rotary letterpress printing
 - + nyloprint® S58 can also be used as a female die for blind embossing
- + **High print quality**
 - + Screen ruling up to 305 lpi (120 L/cm); S43 and S58 for letterpress up to 137 lpi (54 L/cm)
 - + Excellent solid density due to brilliant ink transfer
 - + Reliable and reusable for repeat orders
 - + High durability, suitable for high run lengths
- + **Efficient, consistent and fast plate processing**
 - + Wide exposure latitude
 - + Highly productive and cost effective due to plate processing within 40-50 min

Where printing meets packaging.

nyloprint® S

	nyloprint® S		
	30	43	58
Technical characteristics			
Base material	steel		
Colour of raw plate	green		
Total thickness (mm) (inch)	0.30 (0.012")	0.43 (0.017")	0.58 (0.023")
Plate hardness (Shore D)	96	90	86
Relief depth (mm) (inch)	0.03 (0.001")	0.20 (0.008")	0.32 (0.013")
Tonal range (%) for gravure printing at screen ruling of	5-95 120 l/cm (305 lpi)	5-95 120 l/cm (305 lpi)	5-95 120 l/cm (305 lpi)
Tonal range (%) for letterpress at screen ruling of	-	2-95 54 l/cm (137 lpi)	2-95 54 l/cm (137 lpi)
Distortion factor (mm) (inch)	-	2.08 (5.28")	2.90 (7.37")

Processing parameters¹

Main exposure (min) to be tested	1.0-5.0	1.0-5.0	1.0-5.0
Washout time for pad printing	1-2	1-2	1-3
Washout time for letterpress	-	>3	>4
Washout temperature	20°C / 68°F	20°C / 68°F	20°C / 68°F
Drying time at 80°C / 176°F (min)	15	15	15
Post exposure (min)	2-3	2-3	2-3

Processing Equipment

Suitable equipment	nyloprint® S plate can be processed with nyloprint® processing equipment and all similar devices.
Printing inks	Suitable for commonly used pad printing inks (e.g. UV-inks, solvent-based inks, 2-K inks).
Washout medium	For the washout the solvent nyloprint® R241 np is needed.
Processing information	A detailed description of the individual platemaking steps, as well as detailed information about processing and storing can be found in the nyloprint® User Guide.
High quality standard	nyloprint® printing plates are manufactured according to DIN ISO 9001, DIN ISO 14001 and DIN ISO 50001 standards and requirements. This process ensures our customers consistent high quality products and services.

¹⁾ All processing parameters depend on, among others, the processing equipment and lamp age. The above mentioned processing parameters were established under optimum conditions on nyloprint® processing equipment. Under other conditions the processing times can differ from these. Therefore the above mentioned values are only to be used as a guide.

Please contact us for additional information.

info@xsysglobal.com • www.xsysglobal.com

The aim of our technical documents is to inform and advise our customers. The information provided herein is correct to the best of Flint Group's knowledge. No liability for any errors, facts or opinions is accepted. Customers must satisfy themselves as to the suitability of this product for their application. No responsibility for any loss as a result of any person placing reliance on any material contained herein will be accepted. Product names followed by ® are trademarks registered by Flint Group.