

Be
brilliant.

nyloflex[®] FAH

Versatile flexo plate suited for UV and water based inks



For high quality halftone printing with UV inks

- + Especially developed for high resolution label printing
- + Also suitable for flexible packaging and folding cartons
- + Excellent resistance to UV inks¹
- + Also suitable for solvent and water based inks
- + High ozone resistance
- + Reliable processing and easy handling due to colour change during exposure
- + Brilliant image quality, wide tonal range for reproduction of fine image elements
- + Ideal for printing of fine, homogeneous vignettes
- + Optimum ink coverage in solid areas
- + Reverse elements remain open

Advantages of nyloflex[®] plates

- ✓ Superior printing quality with sharper images, more open intermediate depths, finer highlight dots and less dot gain, i.e. larger range of tonal values therefore improved contrast
- ✓ Increased productivity and data transfer without loss of quality due to digital workflow
- ✓ Consistency in quality when repeating plate processing
- ✓ Cost effective and more environmentally friendly in processing, as no film is required

XSYS
Print solid. Stay flexible.

Where printing meets packaging.

nyloflex® FAH

	nyloflex® FAH		nyloflex® FAH Digital			
	114	170	114	170	254	284
Technical characteristics						
Base material	polyester film		polyester film			
Colour of raw plate	red		red, with black LAMS layer			
Total thickness ² (mm) (inch)	1.14 (0.045")	1.70 (0.067")	1.14 (0.045")	1.70 (0.067")	2.54 (0.100")	2.84 (0.112)
Hardness acc. to DIN 53505 (Shore A)	60	60	60	60	60	60
Plate hardness (Shore A)	77	69	77	69	65	63
Relief depth (mm)	0.6-0.7	0.7-0.9	0.5-0.7	0.7-0.9	0.9-1.2	0.9-1.2
Tonal range (%) at screen ruling (l/cm)	2-95 60	2-95 60	1-98 60	1-98 60	2-98 60	2-98 60
Fine line width (down to µm)	100	100	100	100	100	100
Isolated dot diameter (down to µm)	200	200	200	200	200	200

Processing parameters³

Back exposure (s)	9-24	9-24	9-24	9-24	30-120	45-120
Main exposure (min)	8-15	8-15	8-12	8-12	8-24	8-24
Washout speed (mm/min)	160-180	160-180	160-180	160-180	140-180	130-170
Drying time at 60°C / 140°F (h)	2.0	2.0	2.0	2.0	2.5	2.5-3.0
Post exposure UV-A (min)	10	10	10	10	10	10
Light finishing UV-C (min)	8-12	8-12	8-12	8-12	8-12	8-12

Processing Information

Suitable equipment	The nyloflex® FAH can be processed with nyloflex® processing equipment and all similar devices. The nyloflex® FAH Digital can be used with all laser systems suitable for imaging flexo printing plates.
Printing inks	Suitable for all UV inks as well as water based and solvent based printing inks. ¹ (ethyl acetate content preferably below 15%, ketone content preferably below 5%)
Washout solvents	Especially good results are achieved with nylosolv® washout solvents. nylosolv® can be distilled and reused.
Processing information	A detailed description of the individual platemaking steps, as well as detailed information about processing and storage can be found in the nyloflex® User Guide.
Certification	XSYS printing plates are produced at Willstätt production site, which is certified according to international standards for quality management (DIN EN ISO 9001:2015), environmental management (DIN EN ISO14001:2015) and energy management (DIN EN ISO 50001:2018).

1) Performance with UV inks is dependant on the ink type and temperature - these factors could affect the plate performance and consistency of the print. 2) Standard thicknesses currently available - subject to change. 3) All processing parameters depend on, among others, the processing equipment, lamp age and the type of washout solvent. The above mentioned processing times were established under optimum conditions on nyloflex® processing equipment and using nylosolv® washout solvents. The values for the main exposure of digital plates were determined at an exposure intensity of > 15mW/cm². Under other conditions the processing times can differ from these. Therefore the above mentioned values are only to be used as a guide.

Please contact us for additional information.

info@xsyglobal.com • www.xsyglobal.com

The aim of our technical documents is to inform and advise our customers. The information provided herein is correct to the best of XSYS's knowledge. No liability for any errors, facts or opinions is accepted. Customers must satisfy themselves as to the suitability of this product for their application. No responsibility for any loss as a result of any person placing reliance on any material contained herein will be accepted. Product names followed by ® are trademarks registered by XSYS Germany GmbH and/or its affiliates.



XSYS
Print solid. Stay flexible.