XSYS

Print solid. Stay flexible.

nyloprint®

Poly Chablon

Water washable chablon plates for security and banknote printing



Be brilliant.

HIGHEST PRECISION
AND RELIABLE QUALITY IN SECURITY PRINTING

- Used for inking-up the gravure cylinders in intaglio printing presses.
- Improves the accuracy and print quality especially in high security printing (e.g. bank notes, shares, passports, stamps, etc.).
- Development based on many years of experience in security printing and in close cooperation with users.
- Water washable plates – only pure tap water is needed.
- Optimal ink transfer due to soft relief layer.
- High contrast colour change after exposure gives additional security in the assessment of the plate quality even before washout process.

nyloprint®
Poly Chablon

- For highest dimension stability.
- No defects caused by dust and damaged films.
- No data loss during transfer.
- Smoother plate surface can achieve higher density.
- Highly consistent especially when repeating plate processing.
- No film costs.
- Electronic filing of graphics, film storage is redundant.
- Easy and fast data exchange – worldwide.

nyloprint® poly chablon plates consist of a light sensitive photopolymer layer
BONDED TO STEEL.



FOR SECURITY PRINTING– A MATTER OF TRUST

nyloprint®

Poly chablon plates

Water washable, film-based plate for the high-end label market

Technical characteristics	nyloprint® WS 225[1] hard	nyloprint® WS 230 S soft	nyloprint® WS 230 S Digital soft digital
Base material	steel 0.3 mm (0.012“)		
Colour of raw plate	red		
Total thickness[2] (mm | inch)	2.25 | 0.089″	2.30 | 0.091″	2.30 | 0.091″
Plate hardness (Shore D)	47	27	27
Relief depth (mm | inch)	1.90 | 0.075″	1.95 | 0.077″	1.95 | 0.077″
Fine line width (down to µm)	1	1	1
Isolated dot diameter (down to µm)	2	2	2
Distortion factor (mm | inch)	12.25 | 0.48″	12.56 | 0.49″	12.56 | 0.49″

Processing parameters [3]	
Main exposure at 15 mW/cm³ (min)	15
Washout in brush washer at 45°C / 113° F	12 min / 80 – 100 mm/min
Drying time at 80°C / 176°F (min)	60
Post exposure (min)	10

Processing Equipment

Suitable equipment The nyloprint® WS S plates can be processed with nyloprint® processing equipment and all similar devices. The nyloprint® WS S Digital can be used with all IR-laser systems suitable for imaging letterpress plates. For washout the use of brushes in the washer is recommended..

Washout medium For washout only tap water is needed.

Processing information A detailed description of the individual platemaking steps, as well as detailed information about processing and storing can be found in the nyloprint® User Guide.

Certification XSYS printing plates are produced at Willstätt production site, which is certified according to international standards for quality management (DIN EN ISO 9001:2015), environmental management (DIN EN ISO14001:2015) and energy management (DIN EN ISO 50001:2018).

1) non-standard product 2) Standard thicknesses currently available – subject to change. 3) All processing parameters depend on, among others, the processing equipment and lamp age. The above mentioned processing parameters were established under optimum conditions on nyloprint® processing equipment. Under other conditions the processing times can differ from these. Therefore the above mentioned values are only to be used as a guide.

Please contact us for additional information.
info@xsysglobal.com • www.xsysglobal.com

Our technical documents are designed to inform and guide our customers. The information provided herein is accurate to the best of XSYS's knowledge; however, we accept no liability for any errors, inaccuracies, or opinions expressed. Customers are responsible for determining the suitability of this product for their specific application. XSYS assumes no responsibility for any loss incurred as a result of reliance on the information contained in this document. Product names followed by ® are registered trademarks of XSYS Germany GmbH and/or its affiliates.

XSYS

Print solid. Stay flexible.

02-2025

XSYS

Print solid. Stay flexible.