


XSYS

Print solid. Stay flexible.



nyloflex[®] FTC

For highest print quality in
corrugated post-print



Be
brilliant.

CONVINCING PRINT RESULTS

- **Excellent ink transfer** allows for smooth solids, with even ink laydown, thus improved and consistent print results.
- **Significant fluting** reduction on various corrugated boards.
- **Superior print resolution** – precise reproduction of fine details, sharp and defined elements, text and codes.
- **Reduced bump-up** and consistent dot gain over the whole print run.



SIMPLIFY PREPRESS AND PLATE MAKING

- **Reduce cost, save time:** FTD out of the box - No additional equipment, processing steps or consumables needed.



IMPROVE PRODUCTIVITY AND CONSISTENCY

- **Less dot gain variation** – on press due to flat top dot plate characteristic.
- **Ready to print quickly**, reduced start-up time and waste.
- **Higher productivity** through superior stability at higher press speeds.



Be
brilliant.



nyloflex® FTC

- Inherently flat top flexo plate to cope with all challenges in corrugated postprint.
- Significant fluting reduction on various corrugated boards, from fine to rough flute.
- Suitable for all water based printing inks.



VIBRANT, EYE-CATCHING PRINTS ON EVERY TYPE OF CORRUGATED BOARD



FlatTopDot

nyloflex® FTC Digital

For highest print quality in corrugated post-print



Technical characteristics	nyloflex® FTC Digital				
	284	318	394	470	635
Base Material	Polyester film				
Color of raw plate	Red (with black LAMS layer)				
Total thickness (mm) (inch) ¹	2.84 (0.112)	3.18 (0.125)	3.94 (0.155)	4.70 (0.185)	6.35 (0.250)
Hardness acc. to DIN 53505	32	32	32	32	32
Plate hardness (Shore A)	40	38	36	34	32
Recommended relief depth (mm)	0.9 - 1.2	0.9 - 1.5	1.0 - 1.5	1.2 - 2.2	2.2 - 3.0
Tonal range (%)	2 - 98	2 - 98	3 - 98	3 - 98	3 - 98
at screen ruling (l/cm)	48	48	40	40	32
Fine line width (down to µm)	100	100	300	300	300
Isolated dot diameter (down to µm)	200	200	750	750	750
Processing parameters ²					
Back exposure (s)	20 - 60	20 - 60	50 - 100	50 - 100	50 - 100
Main exposure (min)	10 - 15	10 - 15	10 - 15	10 - 15	10 - 15
Washout speed (mm/min)	130 - 150	100 - 130	100 - 130	80 - 120	60 - 90
Drying time at 60°C / 140°F (h)	2.5 - 3.0	2.5 - 3.0	2.5 - 3.0	3.0 - 3.5	3.0 - 4.0
Post exposure UV-A (min)	10	10	10	10	10
Light finishing UV-C (min) ³	1-4	1-4	1-4	1-4	1-4
Laser intensity (J/cm²)	3.6 J/cm² (depending on Laser manufacturer and model)				

Processing information

Suitable equipment	The nyloflex® FTC Digital can be processed with nyloflex® processing equipment and all similar devices and can be used with all laser systems suitable for imaging flexo printing plates.
Printing inks	The nyloflex® FTC Digital is suitable for all water based printing inks.
Washout solvents	Especially good results are achieved with nylosolv® washout solvents. nylosolv® can be distilled and reused.
Processing information	A detailed description of the imaging, exposure and finishing steps, as well as detailed information about handling and storing, can be found in the nyloflex® User Guide.
Certification	XSYS printing plates are produced at Willstätt production site, which is certified according to international standards for quality management (DIN EN ISO 9001:2015), environmental management (DIN EN ISO14001:2015) and energy management (DIN EN ISO 50001:2018).

1) Standard thicknesses currently available - subject to change 2) All processing parameters depend on, among other things, the processing equipment, lamp age and the type of washout solvent. A minimum exposure intensity of $\geq 17 \text{ mW/cm}^2$ is recommended. The above mentioned processing times were established under optimum conditions in our technical center. The standard test file with 149lpi was imaged at 4000DPI using a ThermoFlexX imager, 20 mW/cm² bank exposure, using nylosolv® A washout solvent and nyloflex® and ThermoFlexX Catena plate processing equipment. Under other conditions the processing times can differ from these; therefore, the above mentioned values are only to be used as a guide. 3) Depending on longevity of the tubes. 4) Suitability with UV inks is dependant on the ink type and temperature - these factors could affect the performance of the plate and consistency of the print.

Please contact us for additional information.
info@xsysglobal.com • www.xsysglobal.com

Our technical documents are designed to inform and guide our customers. The information provided herein is accurate to the best of XSYS's knowledge; however, we accept no liability for any errors, inaccuracies, or opinions expressed. Customers are responsible for determining the suitability of this product for their specific application. XSYS assumes no responsibility for any loss incurred as a result of reliance on the information contained in this document. Product names followed by ® are registered trademarks of XSYS Germany GmbH and/or its affiliates.

XSYS 02-2025
Print solid. Stay flexible.

XSYS

Print solid. Stay flexible.